

Technical Data Sheet

Applications

- Ace machinery & equipment
- Aerospace coatings
- Architectural coatings
- Auto oem
- Auto plastics
- Auto refinish
- Automotive
- Automotive parts & accessories
- Automotive protective coatings
- Commerical printing inks
- Consumer electronics
- Cosmetic ingredients - nails
- General industrial coatings
- Graphic arts
- Industrial maintenance
- Inkjet printing inks
- Metal coatings
- Non-medical housings & hardware for elec
- Paints & coatings
- Personal care ingredients
- Process additives
- Protective coatings
- Truck/bus/rv
- Wood coatings

Product Description

Eastman Cellulose Acetate Butyrate (CAB-321-0.1) is a cellulose ester with a low butyryl content (32.5%) and low molecular weight. It has a viscosity of 0.10 sec and 0.38 poise. Designed for use in automotive basecoats, it is resistant to attack and resistant to redissolve by solvents typical in clearcoats. When CAB-321-0.1 is dissolved in appropriate solvents a clear, colorless solution is produced. It is supplied as a fine white powder.

Eastman CAB-321-0.1 is based on cellulose, one of the most abundant natural renewable resources. The calculated approximate bio-content value of 42% for Eastman CAB-321-0.1 was determined by using six bio-based carbon atoms per anhydroglucose unit divided by the total number of carbons per anhydroglucose unit. Although the value reported is not specifically measured for bio-carbon, it can be estimated based on typical partition data.

Typical Properties

Property	Typical Value, Units
General	
Viscosity ^a	
s	0.1
Poise	0.38
Acetyl Content	17.5 wt %
Butyryl Content	32.5 wt %
Hydroxyl Content	1.3 wt %
Moisture Content	3.0 max %
T _g ^b	127 °C
Specific Gravity	1.2

Refractive Index	1.475
Dielectric Strength	2.5 kv/mil
Tukon Hardness ^c	21 Knoop
Wt/Vol	1.2 kg/L (10 lb/gal)

^aViscosity determined by ASTM Method D 1343. Results converted to poises (ASTM Method D 1343) using the solution density for Formula A as stated in ASTM Method D 817 (20% Cellulose ester, 72% acetone, 8% ethyl alcohol).

^bGlass Transition Temperature

^cASTM D 1474

Comments

Properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

9/21/2022 8:28:02 AM