

Technical Data Sheet

Applications

- uv printing inks
- Aerospace coatings
- Architectural coatings
- Auto oem
- Auto plastics
- Auto refinish
- Automotive
- Automotive protective coatings
- Coil coatings
- Coil coatings-appliances
- Commercial printing inks
- Consumer electronics
- Electronic chemicals
- Flexographic printing inks
- Furniture
- General industrial coatings
- Graphic arts
- Gravure printing inks
- Industrial electronics
- Industrial maintenance
- Inkjet printing inks
- Inks
- Leather coatings
- Marine
- Metal coatings
- Motorcycles
- Non-medical housings & hardware for elec
- Other-transportation
- Overprint varnishes
- Pack & carton coatings
- Packaging coatings non food contact
- Packaging inks non food contact
- Paints & coatings
- Personal care ingredients
- Polymer modification
- Process additives
- Protective coatings
- Roofing
- Screen printing inks
- Small appliances non-food contact
- Truck/bus/rv
- Wood coatings

Product Description

Eastman Cellulose Acetate Butyrate (CAB-381-0.1) is a cellulose ester with medium butyryl content and low viscosity. It was designed for use where low-application viscosities at relatively high solids levels are needed. It is soluble in a wide range of solvents and compatible with many other resins. It will also tolerate the use of solvent blends currently exempt from certain air pollution regulations. When CAB-381-0.1 is dissolved in appropriate solvents a clear, colorless solution is produced. It is supplied as a dry, free-flowing powder.

Eastman CAB-381-0.1 is based on cellulose, one of the most abundant natural renewable resources. The calculated approximate bio-content value of 41% for Eastman CAB-381-0.1 was determined by using six bio-based carbon atoms per anhydroglucose unit divided by the total number of carbons per anhydroglucose unit. Although the value reported is not specifically measured for bio-carbon, it can be estimated based on typical partition data.

For applications that require food contact compliance, please refer to CAB-381-0.1, Food Contact.

Typical Properties

Property	Typical Value, Units
General	
Viscosity ^a	
s	0.1
Poise	0.38
Acetyl Content	13.5 wt %
Butyryl Content	38 wt %
Hydroxyl Content	1.5 wt %
Moisture Content	3.0 max %
T _g ^b	123 °C
Bulk Density	
Poured	458.1 kg/m ³ (28.6 lb/ft ³)
Tapped	544.5 kg/m ³ (34 lb/ft ³)
Specific Gravity	1.2
Acidity	
as Acetic Acid	0.03 wt %
Ash Content	<0.01 %
Refractive Index	1.48
Dielectric Strength	787-984 kv/cm (2-2.5 kv/mil)
Tukon Hardness	18 Knoop
Wt/Vol (Cast Film)	1.2 kg/L (10.0 lb/gal)
Heat Test @ 160°C for 8 hr	Tan melt

^aViscosity determined by ASTM Method D 1343. Results converted to poises (ASTM Method D 1343) using the solution density for Formula A as stated in ASTM Method D 817 (20% Cellulose ester, 72% acetone, 8% ethyl alcohol).

^bGlass Transition Temperature

Comments

Properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

9/21/2022 8:28:24 AM