

# Technical Data Sheet

## Applications

- Ace machinery & equipment
- Adhesives/sealants-b&c
- Aerosol coatings
- Aerospace coatings
- Architectural coatings
- Auto oem
- Auto plastics
- Auto refinish
- Automotive parts & accessories
- Automotive protective coatings
- Coil coatings
- Coil coatings-appliances
- Commerical printing inks
- Consumer electronics
- Electronic chemicals
- Exterior architectural coatings
- General industrial coatings
- Graphic arts
- Gravure printing inks
- Industrial electronics
- Industrial maintenance
- Inkjet printing inks
- Leather coatings
- Metal coatings
- Motorcycles
- Non-medical housings & hardware for elec
- Other-transportation
- Overprint varnishes
- Pack & carton coatings
- Paints & coatings
- Personal care ingredients
- Process additives
- Process solvents
- Protective coatings
- Safety glasses/shield
- Small appliances non-food contact
- Truck/bus/rv
- Water treatment industrial
- Wood coatings

## Product Description

Eastman Cellulose Acetate Butyrate CAB-381-2 is a cellulose ester with medium butyryl content and high viscosity. Other than a higher viscosity and molecular weight, this cellulose ester shares the same general characteristics as CAB-381-0.1 and CAB-381-0.5. CAB-381-2 offers a combination of solubility and compatibility, moisture resistance, excellent surface hardness, and good film strength. When CAB-381-2 is dissolved in appropriate solvents, a clear, colorless solution is produced. It is supplied as a dry, free-flowing powder.

Eastman CAB-381-2 is based on cellulose, one of the most abundant natural renewable resources. The calculated approximate bio-content value of 40% for Eastman CAB-381-2 was determined by using six bio-based carbon atoms per anhydroglucose unit divided by the total number of carbons per anhydroglucose unit. Although the value reported is not specifically measured for bio-carbon, it can be estimated based on typical partition data.

For applications that require food contact compliance, please refer to Eastman CAB-381-2, Food Contact.

# Typical Properties

Property	Typical Value, Units
<b>General</b>	
Viscosity <sup>a</sup>	
s	2
Poise	8
Acetyl Content	13.5 wt %
Butyryl Content	38 wt %
Hydroxyl Content	1.3 wt %
Moisture Content	3.0 max %
T <sub>g</sub> <sup>b</sup>	130 °C
Bulk Density	
Poured	352 kg/m <sup>3</sup> (22 lb/ft <sup>3</sup> )
Tapped	465 kg/m <sup>3</sup> (29 lb/ft <sup>3</sup> )
Specific Gravity	1.2
Acidity	
as Acetic Acid	<0.03 wt % max.
Ash Content	0.05 %
Refractive Index	1.475
Dielectric Strength	787-984 kv/cm (2-2.5 kv/mil)
Tukon Hardness	18 Knoop
Wt/Vol	
(Cast Film)	1.2 kg/L (10.0 lb/gal)
Heat Test	
@ 160°C for 8 hr	Tan melt

<sup>a</sup>Viscosity determined by ASTM Method D 1343. Results converted to poises (ASTM Method D 1343) using the solution density for Formula A as stated in ASTM Method D 817 (20% Cellulose ester, 72% acetone, 8% ethyl alcohol).

<sup>b</sup>Glass Transition Temperature

## Comments

Properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

*Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.*

9/21/2022 8:27:20 AM