

Technical Data Sheet

Applications

- Aerospace coatings
- Architectural coatings
- Auto oem
- Auto refinish
- Automotive
- Automotive parts & accessories
- Commercial printing inks
- Consumer electronics
- Cosmetic ingredients - nails
- Flexographic printing inks
- General industrial coatings
- Graphic arts
- Gravure printing inks
- Industrial maintenance
- Metal coatings
- Non-medical housings & hardware for elec
- Overprint varnishes
- Photographic imaging film
- Screen printing inks
- Truck/bus/rv
- Wood coatings

Product Description

Eastman Cellulose Acetate Butyrate (CAB-553-0.4) is soluble in low molecular weight alcohols (methanol, ethanol, isopropanol, and n-propanol) as well as other common organic solvents. It has a high hydroxyl content (4.8 wt. %, average), which contributes to its alcohol solubility. The hydroxyl group is reactive and may be crosslinked with urea formaldehydes, melamines, and polyisocyanates. When CAB-553-0.4 is dissolved in appropriate solvents a clear, colorless solution is produced. Films of CAB-553-0.4 are colorless and have good ultraviolet stability, maintaining their low color over long periods of time. Eastman Cellulose Acetate Butyrate (CAB-553-0.4) is supplied as a dry, free-flowing powder, offering formulation convenience, ease of handling and maximum formulating flexibility.

Eastman CAB-553-0.4 is based on cellulose, one of the most abundant natural renewable resources. The calculated approximate bio-content value of 41% for Eastman CAB-553-0.4 was determined by using six bio-based carbon atoms per anhydroglucose unit divided by the total number of carbons per anhydroglucose unit. Although the value reported is not specifically measured for bio-carbon, it can be estimated based on typical partition data.

For applications that require food contact compliance, please refer to Eastman CAB-553-0.4, Food Contact.

Typical Properties

Property	Typical Value, Units
General	
Viscosity ^a	
s	0.3
Poise	1.14
Acetyl Content	2.0 wt %
Butyryl Content	47 wt %
Hydroxyl Content	4.8 wt %
Moisture Content	3.0 max %

T _g ^b	136 °C
Specific Gravity	1.20
Tukon Hardness	18 Knoop
Wt/Vol	1.20 kg/L (10.00 lb/gal)

^aViscosity determined by ASTM Method D 1343. Results converted to poises (ASTM Method D 1343) using the solution density for Formula A as stated in ASTM Method D 817 (20% Cellulose ester, 72% acetone, 8% ethyl alcohol).

^bGlass Transition Temperature

Comments

Properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability or fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

9/19/2022 10:27:52 AM